

Mini Review**A review on green silver nanoparticles based on plants: Synthesis, potential applications and eco-friendly approach**

Mohammadlou, M., Maghsoudi, H. and *Jafarizadeh-Malmiri, H.

*Faculty of Chemical Engineering, Sahand University of Technology, Tabriz, Iran***Article history**

Received: 6 December 2014

Received in revised form:

14 July 2015

Accepted: 17 August 2015

Abstract

Silver nanoparticles (AgNPs) are extensively used in various industries due to their unique physico-chemical and antimicrobial properties. Many natural biomolecules in plants (inactivated plant tissue, plant extracts and living plant) such as proteins/enzymes, amino acids, polysaccharides, alkaloids, alcoholic compounds, and vitamins could be involved in bioreduction, formation and stabilization of AgNPs. In this review, the role of plant based biomolecules in the synthesis of AgNPs along with their characteristics, antimicrobial activities and applications are investigated.

© All Rights Reserved

Keywords*Silver nanoparticles**Green synthesis**Nanotechnology**Plant**Antimicrobial properties***Introduction**

Incorporation of green chemistry techniques and methodologies into nanotechnology is of great interest which has gained much attention over the past decade (Hu *et al.*, 2008). Green chemistry which is the use of chemistry principles to reduce or eliminate using of toxic reagents, has resulted to significant reduction in the amount of harmful residues to human health and environment. Green chemistry is defined as chemistry aided processes for pollution prevention which can be extended to specific areas including green analytical chemistry, environmentally friendly analytical chemistry and clean analytical methods (Melchert *et al.*, 2012).

Green synthesis of nanoparticles has attracted considerable attention in recent years. In this regard, plants extracts and natural resources such as microorganisms and enzymes have been found to be good alternative reagents in nanoparticles synthesis. Utilizing green substances has several advantages including low energy consumption and moderate operation conditions (e. g. pressure and temperature) without using any toxic chemicals (Mie *et al.*, 2014). Therefore, green synthesis techniques using various biological organisms such as yeast, mold, algae and bacteria, and plant extracts have been developed for nanoparticles synthesis (Kaviya *et al.*, 2011).

As compared to the metallic elements in bulk state, metallic nanoparticles exhibit unusual chemical, physical, optical and thermal properties due to their

high surface area to volume ratio (Caswell *et al.*, 2003). Therefore, these unique properties make nanoparticles (with diameter smaller than 100 nm) favorable for many different applications (Bhatte *et al.*, 2012).

It is known that silver and its based compounds are highly toxic to major species of microorganisms such as bacteria, fungus and viruses (Sukirtha *et al.*, 2012; Suman *et al.*, 2013; Vadlapudi and Kaladhar, 2014). While the mechanism of bactericidal and fungicidal of silver is not fully known, it has been suggested that silver can inhibit cell transduction and also cause cell lysis (Prabhu and Poulouse, 2012). Silver nanoparticles (AgNPs), due to their surface configuration and small size which in turn, increase their surface to volume ratio, exhibit amazing antimicrobial and physico-chemical properties (Thirumalai Arasu *et al.*, 2010). Antimicrobial activities of silver makes it much interesting choice for application in different areas including water and air treatment, catalysis, mirrors, optics, photography, medical, dentistry, clothing, electronics, and food packaging (Prabhu and Poulouse, 2012; Edison and Sethuraman, 2013).

Many different methods have been developed for synthesis of AgNPs including physical, chemical and green (biological) techniques. In all methods, stabilized nanoparticles are formed by reducing of the silver ions to silver elements using reducing agents followed by nucleation and growing processes (Chen and Yeh, 2002; Sen *et al.*, 2003; Kharissova *et al.*,

*Corresponding author.

Email: h_jafarizadeh@sut.ac.ir; h_jafarizadeh@yahoo.com

Tel: +98-413-345-9099; Fax: +98-413-344-4355

2013). In numerous physical and chemical methods that have been applied to synthesis of nanoparticles, it is possible to obtain particles with the desired characteristics. However the use of expensive and toxic substances as reducing and stabilizing agents makes them unpromising methods (Sharma *et al.*, 2009; Geoprincy *et al.*, 2013).

Green synthesis of AgNPs by microorganisms and plant extracts as an alternative feasible synthesis technique which has gained much attention and application these days. Various metabolites existing in plants including sugars, alkaloids, phenolic acids, terpenoids, polyphenols, and proteins play an important role in the bioreduction of silver ions to silver nanoparticles (Makarov *et al.*, 2014).

The use of *Acalypha indica* (Krishnaraj *et al.*, 2010), mangrove (Gnanadesigan *et al.*, 2011), *Arbutus unedo* (Kouvaris *et al.*, 2012), *Tribulus terrestris* (Gopinath *et al.*, 2012), *Rumex hymenosepalus* (Rodríguez-León *et al.*, 2013), *Eucalyptus chapmaniana* (Sulaiman *et al.*, 2013), *Eucalyptus chapmaniana* (Vadlapudi and Kaladhar, 2014) to synthesis of AgNPs, have already been reported. Polyol components, polysaccharides and water-soluble heterocyclic compounds are the main components of these plant extracts which are mainly responsible for the reduction of silver ions and the stabilization of the produced nanoparticles. In green synthesis of AgNPs using plant extracts, several factors including plant source, types of organic compounds in the crude leaf extract, concentration of initial silver ions, temperature and the type and concentration of leaf extract pigments are the key factors on the efficiency of AgNPs fabrication process (Leela and Vivekanandan, 2008). In comparison with physical and chemical methods, synthesis of nanoparticles by plant extracts is cost effective and eco-friendly method which makes the target nanoparticles safe for human therapeutic uses (Velayutham *et al.*, 2013). This method can be used as an economic and valuable alternative for the large-scale production of AgNPs. Furthermore, extracts from plants may act both as reducing and stabilizing agent in nanoparticle synthesis (Makarov *et al.*, 2014). Using plant extracts can also be advantageous over microorganisms for nanoparticles synthesis, by elimination of the identification, isolation, and maintaining cell cultures processes for microorganisms (Song *et al.*, 2009).

The aim of this study is to (1) describe a green approach for production of AgNPs by using plant extracts; (2) evaluate its advantages and disadvantages as compared to the conventional synthesis methods, and (3) investigate the common techniques to characterize nanoparticles. The main focus is on

the role of the natural plant biomolecules involved in the bioreduction of silver ions and other factors during the nanoparticle synthesis and stabilizing of the AgNPs.

Silver nanoparticles

Among the several noble metal nanoparticles, AgNPs have attracted special attention due to their unique properties including appropriate electrical conductivity, chemical stability, catalytic and antimicrobial activities (Vijay Kumar *et al.*, 2014). Because of high surface to volume ratio, silver in nano-scale has demonstrated completely different properties from bulk particles made from the same material (Thirunavoukkarasu *et al.*, 2013). Therefore, synthesis of AgNPs is an emerging area and interesting subject.

AgNPs are synthesized using various physical, chemical and biological techniques resulting in different shapes and sizes for use in numerous applications. These synthesis methods are categorized into two main categories namely, top-down and bottom-up. In top-down approach, the size of silver metal in its bulk form reduces mechanically to the nano-scale by using sophisticated methodologies such as lithography and laser ablation. Bottom-up approach is also known as self-assembly technique and includes of dissolution of silver salt into a solvent, reduction of silver ions to their element using addition of a reducing agent and then stabilization of the forming AgNPs using a stabilizing agents to prevent agglomeration of nanoparticles (Tolaymat *et al.*, 2010). This approach leads to nanostructures with less defects, more homogenous chemical composition and better short and long range ordering (Leela and Vivekanandan, 2008). Existing top-down and bottom-up techniques for syntheses of AgNPs are summarized in Figure 1.

AgNPs with specific size, shape and morphology can be synthesized by numerous physical and chemical methods including physical adsorption, surface deposition, arc discharge, plasma polymerization, laser CVD (chemical vapor deposition), emulsion polymerization and chemical reduction, thermal decomposition in organic solvents and photo reduction in reverse micelles (Kim *et al.*, 2006; Zhang *et al.*, 2013). In all of these methods, organic solvents, non-biodegradable agents and toxic chemicals may be employed as reducing and stabilizing agents. These chemical reagents are potentially dangerous to the environment and biological systems. Moreover, most of these techniques require complicated controls or hard processing conditions (e.g. temperature and pressure) which make them quite expensive (Zhang




Figure1. Top-down and Bottom- up techniques used to synthesis of AgNPs

et al., 2013). Green synthesis of AgNPs using plant extracts and microorganisms provides significant advantages over the chemical and physical methods. Lower pressure, energy and temperature, non-using toxic chemicals, cost effective, environment friendly and easily scaled up for large scale applications are some of these benefits (Evanoff and Chumanov, 2005).

In green synthesis of AgNPs using plants, plant extracts can be used as reducing agent, capping agent or both (Amin et al., 2012; Ghaffari-Moghaddam and Hadi-Dabanlou, 2014). Additionally, AgNPs can be synthesized by several microorganisms such as the bacterial strains (*Bacillus licheniformis*, *Klebsiella pneumonia*) and fungi strains (*Verticillium* spp, *Fusarium oxysporum* and *Aspergillus flavus*) (Marambio-Jones and Hoek, 2010). Nitrate reductase is an important enzyme in microorganism, especially in fungi which can be act as reducing agent in AgNPs synthesis (Marambio-Jones and Hoek, 2010).

Green synthesis methods of AgNPs

Generally, AgNPs can be synthesized by either green or controlled synthesis processes. A two-step reduction process is utilized in controlled synthesis, while green synthesis involves a three-step process. In first step of controlled synthesis, a strong reducing agent, such as sodium borohydride, is added to the silver salt solution (usually $AgNO_3$) to create small silver particles. In the second step, a weaker reducing agent is applied to increase the size of these small silver particles. This two-step process is used in place of a one-step reduction process because it is easier




Figure 2. Mechanisms of silver nanoparticle green synthesis

to control synthesis for larger AgNPs. Nanoparticle synthesis is often accomplished in the presence of stabilizers to prevent nanoparticles aggregation.

In green synthesis, a solvent (usually water) is chosen and employed in step one. A non-toxic reducing and stabilizer agents are utilized in steps two and three, respectively. In this method, solvents, reducing, and stabilizers agents are selected from natural non-toxic and eco-friendly substances without any adverse effects on the environment (Eshleman et al., 2011). Figure 2, shows the main steps in the green synthesis of metal nanoparticles.

Green synthesis of AgNPs has advantages over conventional methods involving chemical agents associated with environmental toxicity. Generally, green synthesis methods of AgNPs can be classified into polyoxometalates, polysaccharide, Tollens, irradiation, and biological methods which are described in more details in the following sections (Huang and Yang, 2004; Sharma et al., 2009).

Polysaccharide method of AgNPs synthesis

Polysaccharide method is a simple of green synthesis technique which utilizes naturally-occurring polysaccharides as both the reducing and stabilizing agents for the synthesis of metal nanoparticles, especially, gold and AgNPs. In this method, nanoparticles are synthesized in absence of any other chemical reducing agent. As polysaccharides are completely soluble in water, it is used as a solvent in this synthesis method (Huang and Yang, 2004). Several polysaccharides such as starch, chitosan, cellulose and its derivatives are potentially applicable to use in AgNPs synthesis (Hassabo et al., 2015). Among them, chitosan is one of the most important polysaccharide which can be used in AgNPs green synthesis as only reducing agent or as both reducing and stabilizing agents (Huang and Yang, 2004; Travan et al., 2009). The synthesized nanoparticles are highly stable and show no evidence of aggregation after several months of

storage (Huang and Yang, 2004). It is also a simple, low-cost and fast method to prepare chitosan films containing AgNPs (Hebbalalu *et al.*, 2013). Starch is also used as a capping agent and β -D-glucose (starch monomer) as a reducing agent in a gently heated system for synthesis of AgNPs (Sharma *et al.*, 2009). Moreover, cellulose and its derivatives and components (e. g. cellulose powder, microcrystalline cellulose, carboxymethyl cellulose, methyl cellulose and hydroxypropylmethyl cellulose) can participate as both reducing and stabilizing agents in AgNPs synthesis procedures (Hassabo *et al.*, 2015).

Tollens method of AgNPs synthesis

Recently, the Tollens process has been successfully used in AgNPs preparation (Yin *et al.*, 2002). This method is based on $[\text{Ag}(\text{NH}_3)_2]^+$ reduction by aldehydes in an aqueous solution in the presence of ammonia as solvent (Montazer *et al.*, 2012). In the modified Tollens procedure, Ag^+ ions are reduced by saccharides (carbohydrates) in the presence of ammonia to make AgNPs (Sharma *et al.*, 2009). In this method, sodium dodecyl sulfate (SDS) and polyoxyethylenesorbitane monooleate are applied as stabilizers. The main advantage of this method is production of size-controllable AgNPs in a single synthesis step (Eshleman *et al.*, 2011). Due to the higher reactivity of silver compounds, synthesis of separated AgNPs with well-defined shape and well-controlled dimensions is more difficult than gold nanoparticles. The results of Tollens method have indicated that synthesized AgNPs could be very stable for a long time without adding any stabilizer or capping reagent (Le *et al.*, 2010).

Irradiation method of AgNPs synthesis

In this method, bio-organisms with protein are utilized as reducing and capping agents to synthesize stable nanoparticles without a need of reducing agents (Hebbalalu *et al.*, 2013). A new, easy and fast method based on electron irradiation has been developed for the synthesis of nanoparticles (Bogle *et al.*, 2006). This method has been used for synthesis of AgNPs in solution with well-defined size and shape distribution. In this technique a direct laser irradiation is utilized into an aqueous solution of silver salt and a surfactant (as stabilizing agent) in the absence of reducing agents (Abid *et al.*, 2002). A photosensitization technique also uses laser to synthesize AgNPs by using benzophenone. In photosensitization, low laser powers and short irradiation times lead to larger AgNPs (~20 nm) and increased laser powers and longer irradiation times produce smaller AgNPs (~5 nm) (Eshleman *et al.*, 2011).

Ionizing radiation can also reduce silver ions

for AgNPs preparation. Different ionized irradiation such as γ and UV irradiations have been used for AgNPs synthesis (Mafuné *et al.*, 2000; Mallik *et al.*, 2001; Abid *et al.*, 2002; Shin *et al.*, 2004; Bogle *et al.*, 2006; Chen *et al.*, 2007). Gamma irradiation with stabilizer like polyvinyl pyrrolidone (PVP) (Shin *et al.*, 2004), poly-vinyl alcohol (PVA) (Bogle *et al.*, 2006), acetic acid/water solutions containing AgNO_3 and chitosan (Chen *et al.*, 2007) have also been used. Synthesis procedures using microwave irradiation has also been employed using glutathione (Kharissova *et al.*, 2013) and a combination of culture supernatant of *Bacillus subtilis* (Saifuddin *et al.*, 2009). A microwave synthesis of AgNPs by using variable frequency microwave radiation as compared to the conventional heating method. The method increases the reaction rate and gives a higher concentration of AgNPs with the same temperature and exposure (Prabhu and Poulouse, 2012). Irradiation method is not as efficient as controlled synthesis method in controlling the AgNPs size and shape.

Polyoxometalates method of AgNPs synthesis

Polyoxometalates (POMs) are usually poly anions composed of transition metals that have been widely investigated as acid and oxidation catalysts (Maayan *et al.*, 2006). POMs have been extensively used as building blocks of ordered solid materials due to their unique properties such as nano-sized molecular anions, redox and acid catalysis, binding ability to various cations and thermal stability (Uchida *et al.*, 2007). Water is an appropriate solvent for POM synthesis as they dissolve in water. Due to their anionic nature, POMs can reduce silver ions by donating electrons to them. They can also stabilize the AgNPs product (Keita *et al.*, 2009; Sharma *et al.*, 2009). In fact, POMs can also act as both reducing and stabilizer agents (Troupis *et al.*, 2002). Furthermore, POMs have potential to determine the size and shape of the nanoparticles formed in the solution. Therefore, different POMs can be selected to prepare AgNPs with varying sizes and shapes (Eshleman *et al.*, 2011).

Biological method of AgNPs synthesis

In fact, synthesis of metal nanoparticles using microorganisms such as, bacteria, fungi, yeast and actinomycetes has immense potential and is environmental friendly process (Kaler *et al.*, 2010). Extracts from microorganisms including enzymes, proteins, amino acids, polysaccharides and vitamins may take part in AgNPs synthesis as both reducing and capping agents. It seems that microorganisms probably play a role in providing a multitude of

nucleation centers and establish conditions for obtaining highly disperse nanoparticle systems. They have potential to immobilize nanoparticles by providing a viscous medium which in turn, prevents their aggregation. Recently, these microorganisms have been known as possible eco-friendly nanofactories. Several researchers have investigated the biosynthesis of silver and gold nanoparticles using microbial sources (Shaligram *et al.*, 2009). Their results prove that biosynthesis of AgNPs using microorganisms is a cost efficient production method which needs minimum time as compared with the conventional methods. Production of metal nanoparticles by microorganisms is strongly affected by microbial growth stages. The maximum biomass is achieved in mid exponential phase (starting range of stationary phase) of culture along with the maximum synthesis of nanoparticles in the same incubation period (Natrajan *et al.*, 2010). Several studies have been reported successful on biological synthesis of AgNPs using microorganisms including *Verticillium* sp. (Mukherjee *et al.*, 2001; Sastry *et al.*, 2003), *Aspergillus fumigatus* (Bhainsa and D'souza 2006), *Aeromonas* sp. (Fu *et al.*, 2006), *Klebsiella pneumonia*, *Escherichia coli*, *Enterobacter cloacae* (*Enterobacteriaceae*) (Shahverdi *et al.*, 2007), *Aspergillus flavus* (Vigneshwaran *et al.*, 2007) and *Bacillus subtilis* (Saifuddin *et al.*, 2009).

AgNPs synthesis using plants

Metal nanoparticles preparation using plant (inactivated plant tissue, plant extracts and living plant) is an important branch of biosynthesis processes. It has long been known that plants have potential to reduce metal ions both on their surface and in various organs and tissues remote from the ion penetration site (Makarov *et al.*, 2014). Biomolecules existing in plant extracts including, enzymes, proteins, amino acids, vitamins, polysaccharides, and organic acids such as citrates are potentially able to reduce metal ions. In this regard, *in vitro* approaches have been successfully developed in recent years, in which plant extracts are used for the bioreduction of metal ions to form their nanoparticles. The extract of various parts of plants such as leaves, flowers, seeds, barks and roots (Figure 3a) have been applied for synthesis of AgNPs (Bar *et al.*, 2009; Marambio-Jones and Hoek, 2010; Velayutham *et al.*, 2013). The plants extracts may work both as reducing and capping agents in AgNPs synthesis (Figure 3b). These extracts have also been reported to have antibacterial, antidiabetic, anti-inflammatory, antioxidant, anti HIV, snake venom neutralization, antifungal and larvicidal activities (Prabhu *et al.*, 2013).




Figure 3. a) Different parts of plant use in the synthesis of AgNPs. b) Synthesis of AgNPs from plant extracts schematic

Plant metabolites as reducing agent

Various plant metabolites, including terpenoids, polyphenols, sugars, alkaloids, phenolic acids, and proteins play an important role in the bioreduction of metal ions to form nanoparticles (Makarov *et al.*, 2014). Terpenoids are a group of diverse organic polymers synthesized in plants from five-carbon isoprene units which display strong antioxidant activity (Makarov *et al.*, 2014). Flavonoids are a large group of polyphenolic compounds that comprise several classes including, anthocyanins, isoflavonoids, flavonols, chalcones, flavones, and flavanones, which can actively chelate and reduce metal ions into nanoparticles. Various functional groups of flavonoids are capable to form nanoparticle (Makarov *et al.*, 2014). In plant extracts, sugar can also use for the synthesis of metal nanoparticles. It is known that mono saccharides such as glucose, due to their free aldehyde group can act as reducing agents. Furthermore, the reducing ability of disaccharides and polysaccharides depends strongly on their type and concentration of individual monosaccharide components (Makarov *et al.*, 2014). Proteins including different amino acids are capable to reduce several metal ions, resulting their nanoparticles.

Table 1. Different biomolecules of plant extract which act as reducing agent during AgNPs green synthesis

Plant	Biomolecules involved	Experimental conditions	Size (nm)	Refs.
<i>Jatropha curcas</i>	proteins	5/20 ¹ , 1 ² , 80 ³	15-50	(Bar et al., 2009)
<i>Carica papaya</i>	hydroxyflavones and catechins	10/90, 1, room temperature	15	(Jain et al., 2009)
<i>Ocimum sanctum</i>	phenolic and flavonoid compounds, proteins ascorbic acid, Gallic acid, terpenoids,	40/10, 25, 40	Root: 10±2 Stem: 5±1.5	(Ahmad et al., 2010a)
<i>Desmodium triflorum</i>	water-soluble antioxidative agents like ascorbic acids	10/90, 1, room temperature	18	(Ramteke et al., 2013)
<i>Rosa rugosa</i>	carboxylate content amine groups	5/20, 25, room temperature	5-20	(Ahmad et al., 2010b)
<i>Chenopodium album</i>	aldehyde, alkaloids, apocarotenoids, flavonoids	2.5/60, 1, room temperature	12	(Dubey et al., 2010)
<i>Acalypha indica</i>	flavonoids	2/60, 1, room temperature	10-30	(Dwivedi and Gopal, 2010)
<i>Sesuvium portulacastrum</i>	proteins, flavones and terpenoids	12/100, 1, 37	20-30	(Krishnaraj et al., 2010)
<i>Hibiscus rosa sinensis</i>	carboxylate ion groups	5/45, 1, room temperature	5-20	(Nabikhan et al., 2010)
<i>Achyranthus aspera</i>	Polyols	20/25, 0.8, room temperature	13	(Phillip, 2010)
<i>Citrus sinensis</i>	vitamin C, flavonoids, acids and volatile oils	0.3/10, 1, room temperature	20-30	(Daniel et al., 2011)
<i>Mentha piperita</i>	Menthol	3/40, 1, 25 and 60 °C	35 at 25 °C and 10 at 60 °C	(Kaviya et al., 2011)
<i>Citrullus colocynthis</i>	polyphenols with aromatic ring and bound amide region	1.5/30, 1, 28	90	(MubarakAli et al., 2011)
<i>Anacardium occidentale</i>	polyols and proteins	10/90, 1, room temperature	31	(Satyavani et al., 2011)
<i>Zingiber officinale</i>	alkaloids, flavonoids	(2, 3, 4, 5 and 10)/30	15.5	(Sheny et al., 2011)
<i>Piper betle</i>	Proteins	0.59, 100	10	(Singh et al., 2011)
<i>Solanum xanthocarpum</i>	phenolics, alkaloids and sugars	10/190, 1, room temperature	10,20,40, 80 min ?	(Usha Rani and Rajasekharreddy, 2011)
<i>Glycyrrhiza Glabra</i>	flavonoids, terpenoids, thiamine	(2-10)/10, 1, 45	10	(Amin et al., 2012)
<i>Piper nigrum</i>	Proteins	7/100 ,0.5 , 27	20	(Dinesh et al., 2012)
<i>Trianthema decandra</i>	hydroxyflavones and catechins	10/ 50 ,1 , room temperature	5 - 50	(Garg, 2012)
<i>Dioscorea bulbifera</i>	polyphenols or flavonoids	(5, 10, 15)/10 , 1	36-74	(Geethalakshmi and Sarada, 2012)
<i>Elettaria cardamomom</i>	alcohols, carboxylic acids, ethers, esters and aliphatic amines	5/95, 1, room temperature	8-20	(Ghosh et al., 2012)
<i>Leonuri herba</i>	polyphenols and hydroxyl groups	5/20, (different concentration of AgNO ₃), 80	40-70	(Gnanajobitha et al., 2012)
<i>Morinda pubescens</i>	hydroxyflavones, catechins	(1, 2, 3, 4 ,5)/500, 10, 95	9.9-13	(Im et al., 2012)
<i>Olibanum (Boswellia serrata)</i>	hydroxyl , carbonyl	(1, 3 , 5)/10, 1, room temperature	25-50	(Jancy and Inbathamizh, 2012)
<i>Agricultural waste</i>	sugars (aldoses) and terpenoids	various concentrations of gum	7.5 ± 3.8	(Kora et al., 2012)
<i>Annona squamosa</i>	Proteins	121	32 ± 5	(Kumar et al., 2012)
<i>Piper betle</i>	Proteins	10/80	3-37	(Mallikarjuna et al., 2012)
<i>Plumeria rubra</i>	Proteins	50 – 150 (µl)/3, 1, room temperature	3-37	(Patil et al., 2012)
<i>Hydrilla verticillata</i>	Proteins	1/100, (100 ppm AgNO ₃), 28	32 -220	(Sable et al., 2012)
<i>Lantana camara</i>	carbohydrates, glycosides and flavonoids	99/1, 100 , room temperature	65.55	(Sivakumar et al., 2012)
<i>Andrographis paniculata</i>	hydroxyflavones catechins	10/90, 1, room temperature	12.55	(Sulochana et al., 2012)
<i>Annona squamosa</i>	glycoside, alkaloids, saponins, flavonoids, tannins, carbohydrates, proteins, phenolic	10/90, 1, room temperature	28	(Vivek et al., 2012)

<i>Malva parviflora</i>	Proteins	0.4/10, 1, room temperature	19–25	(Zayed <i>et al.</i> , 2012)
<i>Hibiscus cannabinus</i>	ascorbic acid	1/50, 5, 30	9	(Bindhu and Umadevi, 2013)
<i>Castor oil, Khat and Sun flower</i>	proteins, phenols and flavonoids, terpenoids	1.5/30, 1, room temperature	28	(Gebru <i>et al.</i> , 2013)
<i>Artocarpus heterophyllus</i>	amino acids, amides group	(2, 4, 6, 8, and 10%, w/v), 1/4, 6, 121	10.78	(Jagtap and Bapat, 2013)
<i>Cocos nucifera</i>	hydrocarbon such as nonacosane and heptacosane	20/80, 1, 60	23±2	(Roopan <i>et al.</i> , 2013)
<i>Tithonia diversifolia</i>	proteins, polysaccharides, terpenoids	10/90, 10, room temperature	25	(Tran <i>et al.</i> , 2013)
<i>Coleus aromaticus</i>	flavonoids	10/90, 1, room temperature	40–50	(Vanaja and Annadurai, 2013)
<i>Mango</i>	aldehydes, ketone, carboxyl and hydroxyl	3/27, 1, 80	7–27	(Yang and Li, 2013)
<i>Aloe</i>	protein, alkaloids, flavonoids,	10/1+ 10.0 mL	20	(Zhang <i>et al.</i> , 2013)
<i>Syzygium cumini</i>	flavonoids	hydrazine hydrate (20µl to 1 mL per 50 mL), 0.5–5, 35	10–15	(Mittal <i>et al.</i> , 2014)
<i>Tea</i>	amides, carboxyl, amino groups and poly phenols	14.25/750µL AgNO ₃ , 10, room temperature	20-90	(Sun <i>et al.</i> , 2014)

1. Plant extract/AgNO₃ solution (ml/ml)

2. AgNO₃ concentration (mM)

3. Temperature (°C)

Several researchers have been done to biosynthesis of AgNPs by plant extracts. Table 1 summarizes the several different plant extracts and their main biomolecules which act as reducing agent during AgNPs green synthesis.

Plant metabolites as stabilizer agent

Metal nanotriangles have high surface energy making them less stable. Therefore, resulting nanoparticles aggregate and prefer to acquire a more stable morphology, such as a truncated triangle to minimize their Gibbs free energy (Makarov *et al.*, 2014). Therefore, stabilizer agents are usually utilized in nanoparticles synthesis to control the formation and dispersion stability of them (Ahmad *et al.*, 2011). In this regards, it has been suggested that plant hydrocarbons such as nonacosane and heptacosane have a positive effect on stabilization of AgNPs (Roopan *et al.*, 2013). The carbonyl group of amino acid such as lysine, cysteine, arginine, and methionine residues and proteins has potential to bind metal ions to form nanoparticles (e. g. capping of AgNPs) and to prevent agglomeration and thereby stabilize the medium. This suggests that the biological molecules could possibly perform dual functions of formation and stabilization of AgNPs in the aqueous medium (Tran *et al.*, 2013).

Other factors affecting the AgNPs synthesis by plant extracts

Besides the nature of the plant extracts and their active biomolecules types and concentrations, several factors including pH, incubation temperature, reaction time, concentration and electrochemical potential of a metal ion can have effect on metal

ions reduction process (Makarov *et al.*, 2014). Temperature is an important factor which its increases improves the reaction rate and efficiency of nanoparticle synthesis. It seems that an increase in temperature elevates the nucleation rate (Makarov *et al.*, 2014; Vadlapudi and Kaladhar, 2014). The pH value of the plant extracts has a great influence on the formation of nanoparticles. In fact, the charge of natural phytochemicals of the plant extracts changes by variation in pH, affects their ability to bind and reduce metal ions during nanoparticle synthesis. This may affect the shape, size, and yield of formed nanoparticles (Vijayakumar *et al.*, 2013; Makarov *et al.*, 2014). Furthermore, due to the limited ability of plants to reduce metal ions, the efficiency of metal nanoparticle synthesis is influenced by the electrochemical potential of an ion. For example, plant extracts may be reduced ions having a large positive electrochemical potential (e.g., Ag⁺) higher than those with a low electrochemical potential such as ([Ag(S₂O₃)₂]³⁻) (Makarov *et al.*, 2014). The proteins existing in a plant extract can also significantly affect the formation of nanoparticles. The approaches that have recently been used for the green synthesis of metal nanoparticles combine the use of plant extracts with the exogenous supplementation of the in vitro reactions with biomatrices: peptides, and proteins, whose amino acid sequence and structure are optimized for the efficient production of nanoparticles (Makarov *et al.*, 2014).

AgNPs characterization

Nanoparticles are generally characterized by their size, shape, surface area, and dispersity (Mittal *et al.*, 2013). The common techniques to evaluate

Table2. Antimicrobial properties of some of the plants

Name of the plants	Part used	Activity	Against	References
<i>Papaya</i>	Fruit	antibacterial	<i>Escherichia coli</i> and <i>Pseudomonas aeruginosa</i>	(Jain et al., 2009)
<i>Rhizophora apiculata</i> (mangrove)	Dried leaf	antibacterial	<i>Bacillus cereus</i> , <i>Escherichia coli</i> , <i>Klebsiella pneumoniae</i> , <i>Proteus mirabilis</i> , <i>Pseudomonas aeruginosa</i> , <i>Salmonella typhi</i> and <i>Staphylococcus aureus</i>	(Antony et al., 2011)
<i>Citrus sinensis</i>	peel	antibacterial	<i>Escherichia coli</i> , <i>Pseudomonas aeruginosa</i> and <i>Staphylococcus aureus</i>	(Kaviya et al., 2011)
<i>Medicago sativa</i>	seed	antibacterial	Gram positive and gram negative bacteria	(Lukman et al., 2011)
<i>Menth piperita</i>	leaf	antibacterial	clinically isolated human pathogens, <i>Staphylococcus aureus</i> and <i>Escherichia coli</i>	(MubarakAli et al., 2011)
<i>Eclipta prostrate</i>	leaf	larvicidal	<i>filariasis</i> and <i>malaria</i> vectors	(Rajakumar and Abdul Rahuman, 2011)
<i>Euphorbia nivulia</i>	stem latex	antibacterial	both gram negative and gram positive bacteria	(Valodkar et al., 2011)
<i>Tribulus terrestris</i>	fruit	antibacterial	<i>Streptococcus pyogens</i> , <i>Pseudomonas aeruginosa</i> , <i>Escherichia coli</i> , <i>Bacillus subtilis</i> and <i>Staphylococcus aureus</i> .	(Gopinath et al., 2012)
<i>Olibanum</i> (<i>Boswellia serrata</i>)	gum	antibacterial	<i>Staphylococcus aureus</i> , <i>Escherichia coli</i> and <i>Pseudomonas aeruginosa</i>	(Kora et al., 2012)
<i>Acalypha indica</i>	leaf	antifungal	<i>Alternaria alternata</i> , <i>Sclerotinia sclerotiorum</i> , <i>Macrophomina phaseolina</i> , <i>Rhizoctonia solani</i> , <i>Botrytis cinerea</i> and <i>Curvularia Lunata</i>	(Krishnaraj et al., 2012)
<i>Lawsonia inermis</i>	leaf	lousicidal	<i>Pediculus humanus capitis</i> and <i>Bovicola ovis</i>	(Marimuthu et al., 2012)
<i>Prosopis juliflora</i>	leaf	antimicrobial	Gram positive and gram negative bacteria	(Raja et al., 2012)
<i>Pithecellobium dulce</i>	leaf	larvicidal	<i>Culex quinquefasciatus</i>	(Raman et al., 2012)
<i>Cissus quadrangularis</i>	stem	antiparasitic	<i>Hippobosca maculata</i> and <i>Rhipicephalus</i> (<i>Boophilus</i>) <i>microplus</i>	(Santhoshkumar et al., 2012)
<i>Melia azedarach</i>	leaf	anticancer	<i>in vitro</i> HeLa cell lines and lymphoma mice model	(Sukirtha et al., 2012)
<i>Cissus quadrangularis</i>	leaf	antibacterial	bacteria (Gram positive and Gram negative bacteria)	(Valli and Vaseeharan, 2012)
<i>Hibiscus cannabinus</i>	leaf	antibacterial	<i>Escherichia coli</i> , <i>Proteus mirabilis</i> and <i>Shigella flexneri</i>	(Bindhu and Umadevi, 2013)
<i>Pelargonium graveolens</i>	leaf	antibacterial	<i>Klebsiella pneumonia</i> , <i>Shigella someneii</i> , <i>S. flexneri</i> , <i>Pseudomonas aeruginosa</i> , <i>P. mirabilis</i> , and <i>Escherichia coli</i>	(Pandian et al., 2013)
<i>Vitex negundo</i>	leaf	anticancer	HCT15	(Prabhu et al., 2013)
<i>Solanum torvum</i>	fruit	antibacterial antioxidant	<i>Escherichia coli</i> , <i>Pseudomonas</i> and <i>Bacillus spp</i>	(Ramamurthy et al., 2013)
<i>Cocos nucifera</i>	coir	antilarvicidal	<i>Anopheles stephensi</i> and <i>Culex quinquefasciatus</i>	(Roopan et al., 2013)
<i>Morinda citrifolia</i>	root	cytotoxicity	HeLa cell	(Suman et al., 2013)
<i>Desmodium Gangeticum</i>	leaf	antibacterial	<i>Escherichia coli</i>	(Thirunavoukkarasu et al., 2013)
<i>Tithonia diversifolia</i>	leaf	antimicrobial	<i>Pseudomonas aeruginosa</i> , <i>Microbacterium foliorum</i> , <i>Bacillus subtilis</i> , and <i>Rhodococcus equi</i>	(Tran et al., 2013)
<i>Coleus aromaticus</i>	leaf	antibacterial	<i>Bacillus subtilis</i> and <i>Klebsiella planticola</i>	(Vanaja and Annadurai, 2013)
<i>Ficus racemosa</i>	bark	larvicidal	<i>Culex quinquefasciatus</i> and <i>Culex gelidus</i>	(Velayutham et al., 2013)
<i>Artemisia nilagirica</i>	leaf	antibacterial	<i>Staphylococcus aureus</i> , <i>Bacillus subtilis</i> , <i>Escherichia coli</i> , and <i>Proteus subtilis</i>	(Vijayakumar et al., 2013)
<i>Mango</i>	peel	antibacterial	<i>Escherichia coli</i> , <i>Staphylococcus aureus</i> and <i>Bacillus subtilis</i> (spore forming)	(Yang and Li, 2013)
<i>Aloe</i>	leaf	antibacterial	<i>Escherichia coli</i> and <i>Staphylococcus aureus</i>	(Zhang et al., 2013)
<i>Crataegus douglasii</i>	fruit	antibacterial	<i>Staphylococcus aureus</i> and <i>Escherichia coli</i>	(Ghaffari-Moghaddam and Hadi-Dabanlou, 2014)
<i>Caesalpinia Coriaria</i>	leaf	antibacterial	<i>Escherichia coli</i> , <i>Pseudomonas aeruginosa</i> , <i>Klebsiella pneumoniae</i> , and <i>Staphylococcus aureus</i>	(Jeeva et al., 2014)
<i>Syzygium cumini</i>	fruit	anticancer	Dalton lymphoma cell	(Mittal et al., 2014)
<i>Azadirachta indica</i>	leaf	antimicrobial	Gram positive and gram negative bacteria	(Nazeruddin et al., 2014)
<i>Tea</i>	leaf	antibacterial	<i>Escherichia coli</i>	(Sun et al., 2014)
<i>Boerhaavia diffusa</i>	leaf	antibacterial	<i>Aeromonas hydrophila</i> , <i>Pseudomonas fluorescens</i> and <i>Flavobacterium branchiophilum</i>	(VijayKumar et al., 2014)
<i>Ocimum tenuiflorum</i>	Leaf	antimicrobial	<i>Staphylococcus aureus</i> ,	(Logeswari et al., 2015)
<i>Solanum tricobatum</i>	Leaf		<i>Pseudomonas aeruginosa</i> ,	
<i>Syzygium cumini</i>	leaf		<i>Escherichia coli</i> and <i>Klebsiella pneumonia</i>	
<i>Centella asiatica</i>	leaf			
<i>Citrus sinensis</i>	peel			

nanoparticles characteristics can be classified into two main groups namely; quantitative and qualitative. These methods include a range of various sophisticated techniques like, dynamic light scattering (DLS), scanning electron microscopy (SEM), energy dispersive spectroscopy (EDS), UV–vis spectroscopy, transmission electron microscopy (TEM), X-ray diffraction (XRD), fourier transform infrared spectroscopy (FT-IR), surface enhanced raman spectroscopy (SERS), atomic force microscopy (AFM), high angle annular dark field (HAADF), atomic absorption spectroscopy (AAS), inductively coupled plasma (ICP) and X-ray photoelectron spectroscopy (XPS) (Rajasekharreddy *et al.*, 2010; Mittal *et al.*, 2013). AgNPs characteristics can be studied using some of these techniques which in turn, are helpful to resolve diverse parameters such as particle size, shape, crystallinity, fractal dimensions, pores size and surface area (Ingale and Chaudhari, 2013).

Qualitative analysis

FT-IR

FT-IR is a molecular vibrational spectroscopy that dissects chemical functional groups in different absorbance regions between 4000 and 400 cm^{-1} (Meng *et al.*, 2014). FT-IR measurements are carried out to identify the possible biomolecules responsible for reduction, capping and efficient stabilization of AgNPs and the local molecular environment of the capping agents on the nanoparticle (Chanda, 2013).

UV–vis spectrophotometry

UV–vis spectroscopy refers to absorption spectroscopy in the UV–vis spectral region. Light wave lengths in the 300–800 nm are generally used for characterizing various metal nanoparticles in the size range of 2 to 100 nm (Mittal *et al.*, 2013). UV–vis spectroscopy is an important technique to determine the formation and stability of AgNPs in aqueous solution (Bar *et al.*, 2009; Philip *et al.*, 2011). Spectrophotometric absorption measurement in the wavelength ranging from 400 to 450 nm is used to characterize AgNPs (Mittal *et al.*, 2013; Mittal *et al.*, 2014).

SEM

SEM is a technique that uses electrons instead of light to form an output image (Klein *et al.*, 2012). The SEM analysis is employed to characterize the size, shape, morphology and distribution of synthesized AgNPs (Chanda, 2013). The SEM micrographs also indicate the purity and polydispersity of resulting AgNPs (Mittal *et al.*, 2013).

XRD

XRD is a useful tool in obtaining information about the atomic structure of materials. XRD is not only usually used for qualitative identification of minerals in geological samples by fingerprinting approach but also is used for the quantification of mineralogical data (Al-Jaroudi *et al.*, 2007). XRD is a valuable characterization tool to prove the formation of AgNPs, determine the crystal structure and calculate the crystalline nanoparticle size (Philip, 2010; Chanda, 2013).

AFM

The shape, size and surface area of the synthesized AgNPs are studied using AFM (Mohan Kumar *et al.*, 2012). The improvement of AFM over conventional microscopes such as SEM and TEM is that AFM technique makes three dimensional images so that particle height and volume can be intended (Ingale and Chaudhari, 2013).

SERS

The Raman spectrum of the nanoparticle solution is recorded to detect the possible functional groups of capping agents participated in stabilization of the nanoparticles (Kora *et al.*, 2012). Surface enhanced Raman spectroscopy is a popular technique in bioanalytical chemistry and a potentially powerful enabling technology for *in vitro* diagnostics. In fact, SERS combines the excellent chemical specificity of Raman spectroscopy with the good sensitivity provided by enhancement of the signal that is observed when the analyzed molecule lies over (or very close to) the surface of metal nanoparticles (Morasso *et al.*, 2014).

The modern modification of Raman spectroscopy, SERS, utilizes generation of very strong electromagnetic field resulting from exciting of the localized surface plasmons in the metallic nanoparticles. SERS spectrum is observed if a molecule is in a close contact with a SERS-active support. Nowadays, SERS has been widely used in detection, identification and monitoring various biochemical processes since this technique has fast, label-free and non-invasive nature together with its high molecular specificity and sensitivity. First of all, SERS provides valuable information on the adsorption mechanism of a (bio) molecule on a metallic surface pointing what functional groups or atoms participate in metal–adsorbate interactions (Jaworska and Malek, 2014).

Color

Usually change in color of the aqueous salt

solution of a metal is indicative of metal nanoparticle formation. Distinct color change of the silver nitrate solution from colorless to gray color after reduction process indicates formation of AgNPs (Chen *et al.*, 2009).

Quantitative analysis

TEM

TEM is a useful real-space analysis method and helps to observe the particle size of a material in nano-scale and to study the crystal structure meticulously with highest resolution (Tanaka, 2008). TEM measurements are conducted in order to estimate the particle size and size distribution of the synthesized AgNPs (Chanda, 2013).

DLS

Dynamic light scattering (DLS) technique as a diagnostic tool for particle size distribution (PSD) profile of AgNPs in solution or colloidal suspensions has been widely used in science and industry (Li *et al.*, 2014). DLS is defined as a technique by changing the scattering light intensity fluctuation to obtain the sample average hydrodynamic diameter. Real-time monitoring nanoparticles size can be realized by DLS because the measurement process of DLS is rapid and sensitive solution phase detection. Currently, this technique has been applied to detect metal ions and cancer biomarkers (Ma *et al.*, 2014).

HAADF

Several electron microscopy techniques such as high angle annular dark field (HAADF) are used to study the mechanism by which AgNPs interact with bacteria. The size distribution of the nanoparticles interacting with each type of bacteria was obtained from the HAADF images (Morones *et al.*, 2005). HAADF is a powerful technique for analysis of biological samples, such as proteins, and bacteria interfaced with inorganic nanoparticles. HAADF images are mainly formed by electrons that have undergone Rutherford backscattering. As a result, image contrast is related to differences in atomic number with intensity varying as $\sim Z^2$ (Elechiguerra *et al.*, 2005).

ICP

The detection capabilities of single particle inductively coupled plasma-mass spectrometry (SPICPMS) with respect to particle size and number concentrations can be investigated for the case of AgNPs (Tuoriniemi *et al.*, 2012). Ag concentrations in the deionized and the original AgNPs solutions

can be determined by ICP spectrometry (Kim *et al.*, 2009). The resulting silver concentration is measured by either inductively coupled plasma (ICP) emission spectroscopy (ES) or ICP mass spectrometry (MS) (Pal *et al.*, 2007).

XPS

The X-ray photoelectron spectroscopy (XPS) measurements have been carried out to clarify the surface chemical states of the nanoparticles (Ashida *et al.*, 2007). AgNPs are investigated by XPS to characterize the nature of the surfactant chemisorbed to the surface (Wilson and Langell, 2014). It is used to examine the valence of the resulting AgNPs while it also provides further information regarding the structure of the AgNPs encapsulated in the organic network (Xiong *et al.*, 2013).

Antimicrobial properties of AgNPs

It is well known that silver-based compounds are highly toxic to microorganisms showing strong biocidal effects on more than 16 species of bacteria including *Escherichia coli*, *Bacillus subtilis*, *Vibria cholera*, *Pseudomonas aeruginosa*, *Syphilis typhus*, and *Staphylococcus aureus*. Moreover, it has proven to be active against several types of viruses such as hepatitis B virus and herpes simplex virus (Sondi and Salopek-Sondi, 2004; Galdiero *et al.*, 2011). It is suggested that silver's mode of action depends strongly on Ag^+ ions which intensely prevent bacterial growth through suppression of respiratory enzymes and electron transport components and through interference with DNA functions (Galdiero *et al.*, 2011). The results of many different studies have shown that the membrane permeability and respiratory function can be affected by attaching silver ions to cell surface. Another probable phenomenon is that silver not only have a close interaction with the surface of the membrane, but can also penetrate deep inside the bacteria. Furthermore, it is believed that DNA loses its replication ability in the presence of silver ions (Sondi and Salopek-Sondi, 2004). Several studies have indicated that the silver has relatively higher antimicrobial activity against gram negative bacteria than gram positive bacteria, which may be attributed to the thinner peptidoglycan layer and the presence of beta barrel proteins called porins in their cell wall structure (Geoprincy *et al.*, 2013).

Among noble metal nanoparticles, AgNPs have gained wide applications in different fields due to their strong antimicrobial activities (Valli and Vaseeharan, 2012; Ghaffari-Moghaddam and Hadi-Dabanlou, 2014; Jeeva *et al.*, 2014; VijayKumar *et al.*, 2014). The high specific surface to volume ratio of

AgNPs increases their contact with microorganisms, promoting the dissolution of silver ions and hence improving biocidal effectiveness. The bactericidal activity of AgNPs is achieved by the ability of AgNPs to release silver ions (Vijaykumar *et al.*, 2013).

The surface of AgNPs can easily form a layer of water and thus many silver ions can be released from AgNPs into the water. On the other hand, the main composition of bacteria cell membrane is phospholipid bilayers and protein molecules having negative electricity which make the whole cell membrane negatively charged. Therefore, the silver ions with positive electricity have the ability to attach to bacteria cell membrane quickly, which alters or damages the structures of bacteria. Moreover, Ag⁺ ions can be attracted to the sulfhydryl group (SH) of bacterial enzymes (respiratory enzymes), making the enzymes inactivated and even died out (Zhang *et al.*, 2013).

The AgNPs antimicrobial activity depends strongly on several factors including type of microorganisms, temperature, pH and AgNO₃ concentration (Marambio-Jones and Hoek, 2010). It is inversely proportional to the Ag⁺ concentration. This can be attributed to the fact that smaller particles have larger surface area available for interaction and will give more bactericidal effects than the larger particles (Chanda, 2013). Antimicrobial activities of the synthesized AgNPs can be evaluated using the standard micro-dilution method, determining the minimum inhibitory concentration (MIC) which leads to inhibition of bacterial growth. The minimum bactericidal concentration (MBC) can be characterized as the minimum concentration of the sample required to achieve irreversible inhibition, such as killing the bacteria after a defined period of incubation (Panáček *et al.*, 2006). Table 2, shows some of the plants and their antimicrobial properties.

Potential applications of AgNPs

Nowadays, many industries utilize the specific and unique properties of silver materials in their products such as clothing, respirators, household water filters, antibacterial sprays, cosmetics, detergent, dietary supplements, cutting boards, sox, shoes, cell phones, laptop keyboards and children's toys (Jeeva *et al.*, 2014). Furthermore, AgNPs have been widely incorporated in surgical instruments, wound dressings, bond prosthesis and heart valves, electronics, and biosensing. In addition, AgNPs are applied in or on the surface of various textiles, laundry additives, room sprays, water cleaners, nano-device manufacture and food storage containers (Vivek *et al.*, 2012; Roopan *et al.*, 2013).

Topical ointments and creams containing silver to avoid infection of burns and open wounds are examples in the field of medical industries where the most widely used and known applications of silver materials and AgNPs are seen (Song and Kim, 2009). AgNPs have potentially antimicrobial effects against infectious organisms such as *Escherichia coli* (Thirunavoukkrasu *et al.*, 2013). Additionally, in the case of drug delivery applications, the noble metal nanoparticles such as AgNPs are powerful and promising tools due to existing functionalized surface. In other words, the unique properties of AgNPs such as large surface to volume ratio, absorption in the visible range, surface functionalization, and controlled drug release make them valuable in human life studies (Mittal *et al.*, 2014). AgNPs ensure safety of food and preserve food for longer periods by killing the microorganisms when they are used in the packaging of them (Das *et al.*, 2008). Additionally, packaging films and coatings having AgNPs are able to adsorb and decompose ethylene which is a natural plant hormone produced during ripening process. Removing ethylene from a package environment helps the fresh produce like fruits and vegetables to have a longer shelf life (Silvestre *et al.*, 2011).

In addition to human life related applications, the unique chemical and physical properties of nanoparticles make them extremely suitable for other high-tech applications such as designing new and improved sensing devices especially electrochemical sensors and biosensors. In this regard, AgNPs and certain core-shell metal nanoparticles have also been utilized in electro analysis by the labeling of biomolecules. In the literature, it has been revealed that an electrochemical DNA biosensor based on AgNPs label could sense the target oligonucleotides at levels as low as 0.5 pM (Luo *et al.*, 2006). AgNPs have good electrical conductivity and hence they can also act as the electron transfer enhancer between proteins and electrodes. Furthermore, researches obtained results indicating that AgNPs can also be utilized as the electrical bridge for the electron transfer between cytochrome c and the electrode (Liu *et al.*, 2003; Luo *et al.*, 2006).

Future of green AgNPs based on plants

Chemical and physical methods for synthesis of AgNPs have been followed over the decades. The use of expensive procedures and various toxic chemicals in their synthesis processes makes the biological synthesis the more preferred alternative (Prabhu and Poulouse, 2012). Microbial synthesis is readily scalable, environmentally benign and biocompatible. However, production of microorganisms is often

more expensive than the plant extracts. Results of several studies have indicated that AgNPs synthesized by plants have more stability in comparison with those produced by microorganisms. Shape and size of nanoparticles could be controlled with the use of plants. However, AgNPs synthesis mechanism by plants is quite complex to understand (Geoprincy *et al.*, 2013). Additionally, plant extracts are able to reduce metal ions faster than fungi or bacteria (Iravani, 2011). Furthermore, these processes can also be easily scaled up (Vadlapudi and Kaladhar, 2014). The AgNPs synthesized based on plants are utilized in many applications beneficial to humans. The use of environmentally benign materials like plant extracts in the synthesis of AgNPs offers numerous pharmaceutical and biomedical applications due to the absence of toxic chemical in the synthesis procedures. Therefore, AgNPs applications in drug delivery systems might be the future thrust in the field of medicine.

Conclusion

Natural sources have the potential to reduce silver ions into AgNPs. It is understood that the variety of natural compounds that are present in plant extracts can act as both reducing and stabilizing agents for synthesis of AgNPs. Plants mediated AgNPs are stable due to the presence of natural capping agents such as proteins which prevent the particles from aggregation. Green synthesis of AgNPs using plant extracts has several advantages such as eco-friendliness, biocompatibility and cost-effectiveness. It is concluded that due to these unique properties, AgNPs will have a key role in many of the nanotechnology based processes.

References

- Abid, J., Wark, A., Brevet, P. and Girault, H. 2002. Preparation of silver nanoparticles in solution from a silver salt by laser irradiation. *Chemical Communications* 7: 792-793.
- Ahmad, M. B., Tay, M. Y., Shameli, K., Hussein, M. Z. and Lim, J. J. 2011. Green synthesis and characterization of silver/chitosan/polyethylene glycol nanocomposites without any reducing agent. *International journal of Molecular Sciences* 12(8): 4872-4884.
- Ahmad, N., Sharma, S., Alam, M. K., Singh, V., Shamsi, S., Mehta, B. and Fatma, A. 2010a. Rapid synthesis of silver nanoparticles using dried medicinal plant of basil. *Colloids and Surfaces B: Biointerfaces* 81(1): 81-86.
- Ahmad, N., Sharma, S., Singh, V., Shamsi, S., Fatma, A. and Mehta, B. 2010b. Biosynthesis of silver nanoparticles from *Desmodium triflorum*: a novel approach towards weed utilization. *Biotechnology Research International* doi:10.4061/2011/454090.
- Al-Jaroudi, S. S., Ul-Hamid, A., Mohammed, A.-R. I. and Saner, S. 2007. Use of X-ray powder diffraction for quantitative analysis of carbonate rock reservoir samples. *Powder Technology* 175(3): 115-121.
- Amin, M., Anwar, F., Janjua, M. R. S. A., Iqbal, M. A. and Rashid, U. 2012. Green synthesis of silver nanoparticles through reduction with *Solanum xanthocarpum* L. berry extract: characterization, antimicrobial and urease inhibitory activities against *Helicobacter pylori*. *International Journal of Molecular Sciences* 13(8): 9923-9941.
- Antony, J.J., Sivalingam, P., Siva, D., Kamalakkannan, S., Anbarasu, K., Sukirtha, R., Krishnan, M. and Achiraman, S. 2011. Comparative evaluation of antibacterial activity of silver nanoparticles synthesized using *Rhizophora apiculata* and glucose. *Colloids and Surfaces B: Biointerfaces* 88(1): 134-140.
- Ashida, T., Miura, K., Nomoto, T., Yagi, S., Sumida, H., Kutluk, G., Soda, K., Namatame, H. and Taniguchi, M. 2007. Synthesis and characterization of Rh (PVP) nanoparticles studied by XPS and NEXAFS. *Surface Science* 601(18): 3898-3901.
- Bar, H., Bhui, D. K., Sahoo, G. P., Sarkar, P., Pyne, S. and Misra, A. 2009. Green synthesis of silver nanoparticles using seed extract of *Jatropha curcas*. *Colloids and Surfaces A: Physicochemical and Engineering Aspects* 348(1): 212-216.
- Bhainsa, K. C., and D'souza, S. 2006. Extracellular biosynthesis of silver nanoparticles using the fungus *Aspergillus fumigatus*. *Colloids and Surfaces B: Biointerfaces* 47(2): 160-164.
- Bhatte, K. D., Deshmukh, K. M., Patil, Y. P., Sawant, D. N., Fujita, S.-I., Arai, M. and Bhanage, B. M. 2012. Synthesis of powdered silver nanoparticles using hydrogen in aqueous medium. *Particuology* 10(1): 140-143.
- Bindhu, M. and Umadevi, M. 2013. Synthesis of monodispersed silver nanoparticles using *Hibiscus cannabinus* leaf extract and its antimicrobial activity. *Spectrochimica Acta Part A: Molecular and Biomolecular Spectroscopy* 101: 184-190.
- Bogle, K., Dhole, S. and Bhoraskar, V. 2006. Silver nanoparticles: synthesis and size control by electron irradiation. *Nanotechnology* 17(13): 3204-3208.
- Caswell, K., Bender, C. M. and Murphy, C. J. 2003. Seedless, surfactantless wet chemical synthesis of silver nanowires. *Nano Letters* 3(5): 667-669.
- Chanda, S. 2013. Silver nanoparticles (medicinal plants mediated) : A new generation of antimicrobials to combat microbial pathogens- a review. In Méndez-Vilas, A. (Ed). *Microbial pathogens and strategies for combating them: science, technology and education*, p. 1314-1323. Spain: Formatex.
- Chen, D., Qiao, X., Qiu, X. and Chen, J. 2009. Synthesis and electrical properties of uniform silver nanoparticles for electronic applications. *Journal of Materials Science* 44(4): 1076-1081.

- Chen, P., Song, L., Liu, Y. and Fang, Y. 2007. Synthesis of silver nanoparticles by γ -ray irradiation in acetic water solution containing chitosan. *Radiation Physics and Chemistry* 76(7): 1165-1168.
- Chen, Y. and Yeh, C. 2002. Laser ablation method: use of surfactants to form the dispersed Ag nanoparticles. *Colloids and Surfaces A: Physicochemical and Engineering Aspects* 197(1): 133-139.
- Morasso, C., Mehn, D., Vanna, R., Bedoni, M., Colombo, M., Prosperi, D. and Gramatica, F. 2014. One-step synthesis of star-like gold nanoparticles for surface enhanced Raman spectroscopy. *Materials Chemistry and Physics* 143: 1215-1221.
- Daniel, S. K., Ayyappan, S., Philippan, N. J. P., Sivakumar, M., Menaga, G. and Sironmani, T. A. 2011. Green synthesis and transfer of silver nanoparticles in a food chain through Chironomid larva to Zebra fish - A new approach for therapeutics. *International Journal of Nanoscience and Nanotechnology* 2: 159-169.
- Das, M., Saxena, N. and Dwivedi, P. D. 2008. Emerging trends of nanoparticles application in food technology: Safety paradigms. *Nanotoxicology* 3(1): 10-18.
- Dinesh, S., Karthikeyan, S. and Arumugam, P. 2012. Biosynthesis of silver nanoparticles from *Glycyrrhiza glabra* root extract. *Archives of Applied Science Research* 4(1): 178-187.
- Dubey, S. P., Lahtinen, M. and Sillanpää, M. 2010. Green synthesis and characterizations of silver and gold nanoparticles using leaf extract of *Rosa rugosa*. *Colloids and Surfaces A: Physicochemical and Engineering Aspects* 364(1): 34-41.
- Dwivedi, A. D. and Gopal, K. 2010. Biosynthesis of silver and gold nanoparticles using *Chenopodium album* leaf extract. *Colloids and Surfaces A: Physicochemical and Engineering Aspects* 369(1): 27-33.
- Edison, T. and Sethuraman, M. 2013. Biogenic robust synthesis of silver nanoparticles using *Punica granatum* peel and its application as a green catalyst for the reduction of an anthropogenic pollutant 4-nitrophenol. *Spectrochimica Acta Part A: Molecular and Biomolecular Spectroscopy* 104: 262-264.
- Elechiguerra, J. L., Burt, J. L., Morones, J. R., Camacho-Bragado, A., Gao, X., Lara, H. H. and Yacaman, M. J. 2005. Interaction of silver nanoparticles with HIV-1. *Journal of Nanobiotechnology* 3(6): 1-10.
- Eshleman, E., Nagid, B. and Ozanne, M. 2011. Silver Nanoparticles: Past, Production, and Potential. Downloaded from <http://www.eoearth.org/view/article/171741/> on 16/11/2014.
- Evanoff, D. D. and Chumanov, G. 2005. Synthesis and optical properties of silver nanoparticles and arrays. *A European Journal of Chemical Physics and Physical Chemistry* 6(7): 1221-1231.
- Fu, M., Li, Q., Sun, D., Lu, Y., He, N., Deng, X., Wang, H. and Huang, J. 2006. Rapid preparation process of silver nanoparticles by bioreduction and their characterizations. *Chinese Journal of Chemical Engineering* 14(1): 114-117.
- Galdiero, S., Falanga, A., Vitiello, M., Cantisani, M., Marra, V. and Galdiero, M. 2011. Silver nanoparticles as potential antiviral agents. *Molecules* 16(10): 8894-8918.
- Garg, S. 2012. Rapid biogenic synthesis of silver nanoparticles using black pepper (*Piper nigrum*) corn extract. *International Journal of Innovations in Biological and Chemical Sciences* 3: 5-10.
- Gebru, H., Tadesse, A., Kaushal, J. and Yadav, O. 2013. Green synthesis of silver nanoparticles and their antibacterial activity. *Journal of Surface Science and Technology* 29: 47-66.
- Geethalakshmi, R. and Sarada, D. 2012. Gold and silver nanoparticles from *Trianthema decandra*: synthesis, characterization, and antimicrobial properties. *International Journal of Nanomedicine* 7: 5375-5384.
- Geoprincy, G., Srri, B. V., Poonguzhali, U., Gandhi, N. N. and Renganathan, S. 2013. A review on green synthesis of silver nano particles. *Asian Journal of Pharmaceutical and Clinical Research* 6(1): 8-12.
- Ghaffari-Moghaddam, M., and Hadi-Dabanlou, R. 2014. Plant mediated green synthesis and antibacterial activity of silver nanoparticles using *Crataegus douglasii* fruit extract. *Journal of Industrial and Engineering Chemistry* 20(2): 739-744.
- Ghosh, S., Patil, S., Ahire, M., Kitture, R., Kale, S., Pardesi, K., Cameotra, S. S., Bellare, J., Dhavale, D. D. and Jabgunde, A. 2012. Synthesis of silver nanoparticles using *Dioscorea bulbifera* tuber extract and evaluation of its synergistic potential in combination with antimicrobial agents. *International Journal of Nanomedicine* 7: 483-496.
- Gnanadesigan, M., Anand, M., Ravikumar, S., Maruthupandy, M., Vijayakumar, V., Selvam, S., Dhineshkumar, M. and Kumaraguru, A. 2011. Biosynthesis of silver nanoparticles by using mangrove plant extract and their potential mosquito larvicidal property. *Asian Pacific Journal of Tropical Medicine* 4(10): 799-803.
- Gnanajobitha, G., Annadurai, G. and Kannan, C. 2012. Green synthesis of silver nanoparticle using *Elettaria cardamomom* and assesment of its antimicrobial activity. *International Journal of Pharma Sciences and Research* 3: 323-330.
- Gopinath, V., MubarakAli, D., Priyadarshini, S., Priyadharsshini, N. M., Thajuddin, N. and Velusamy, P. 2012. Biosynthesis of silver nanoparticles from *Tribulus terrestris* and its antimicrobial activity: A novel biological approach. *Colloids and Surfaces B: Biointerfaces* 96: 69-74.
- Gopinath, S. M., Saha, N. S., V, J. J., Khanum, N. S., Ganesh, S. and Ashwini Patil, G. M. 2013. Biological synthesis, characterization and application of silver nano particles - A review. *International Journal of Pharmaceutical Applications* 4(1): 19-28.
- Hassabo, A. G., Nada, A. A., Ibrahim, H. M. and Abou-Zeid, N. Y. 2015. Impregnation of silver nanoparticles into polysaccharide substrates and their properties. *Carbohydrate Polymers* 122: 343-350.
- Hebbalalu, D., Lalley, J., Nadagouda, M. N. and Varma, R. S. 2013. Greener techniques for the synthesis of silver nanoparticles using plant extracts, enzymes, bacteria,

- biodegradable polymers, and microwaves. *ACS Sustainable Chemistry & Engineering* 1(7): 703-712.
- Hu, B., Wang, S.-B., Wang, K., Zhang, M. and Yu, S. 2008. Microwave-assisted rapid facile "green" synthesis of uniform silver nanoparticles: self-assembly into multilayered films and their optical properties. *The Journal of Physical Chemistry C* 112(30): 11169-11174.
- Huang, H. and Yang, X. 2004. Synthesis of polysaccharide-stabilized gold and silver nanoparticles: a green method. *Carbohydrate Research* 339(15): 2627-2631.
- Im, A., Han, L., Kim, E., Kim, J., Kim, Y. S. and Park, Y. 2012. Enhanced antibacterial activities of Leonuri Herba extracts containing silver nanoparticles. *Phytotherapy Research* 26(8): 1249-1255.
- Ingale, A. G. and Chaudhari, A. 2013. Biogenic synthesis of nanoparticles and potential applications: An eco-friendly approach. *Journal of Nanomedicine & Nanotechnology* 4: 165-170.
- Iravani, S. 2011. Green synthesis of metal nanoparticles using plants. *Green Chemistry* 13(10): 2638-2650.
- Jagtap, U. B. and Bapat, V. A. 2013. Green synthesis of silver nanoparticles using *Artocarpus heterophyllus* Lam. seed extract and its antibacterial activity. *Industrial Crops and Products* 46: 132-137.
- Jain, D., Daima, H. K., Kachhwaha, S. and Kothari, S. 2009. Synthesis of plant-mediated silver nanoparticles using papaya fruit extract and evaluation of their anti microbial activities. *Digest journal of Nanomaterials and Biostructures* 4(3): 557-563.
- Jancy, M. E. and Inbathamizh, L. 2012. Green synthesis and characterization of nano silver using leaf extract of *Morinda pubescens*. *Asian Journal of Pharmaceutical and Clinical Research* 5(1): 159-162.
- Jaworska, A. and Malek, K. 2014. A comparison between adsorption mechanism of tricyclic antidepressants on silver nanoparticles and binding modes on receptors. Surface-enhanced Raman spectroscopy studies. *Journal of Colloid and Interface Science* 431: 117-124.
- Jeeva, K., Thiyagarajan, M., Elangovan, V., Geetha, N. and Venkatachalam, P. 2014. *Caesalpinia coriaria* leaf extracts mediated biosynthesis of metallic silver nanoparticles and their antibacterial activity against clinically isolated pathogens. *Industrial Crops and Products* 52: 714-720.
- Kaler, A., Patel, N. and Banerjee, U. C. 2010. Green synthesis of silver nanoparticles. *Current Research & Information on Pharmaceutical Sciences* 11(4): 68-71.
- Kaviya, S., Santhanalakshmi, J., Viswanathan, B., Muthumary, J. and Srinivasan, K. 2011. Biosynthesis of silver nanoparticles using citrus sinensis peel extract and its antibacterial activity. *Spectrochimica Acta Part A: Molecular and Biomolecular Spectroscopy* 79(3): 594-598.
- Keita, B., Liu, T. and Nadjo, L. 2009. Synthesis of remarkably stabilized metal nanostructures using polyoxometalates. *Journal of Materials Chemistry* 19(1): 19-33.
- Kharissova, O. V., Dias, H., Kharisov, B. I., Pérez, B. O. and Pérez, V. M. J. 2013. The greener synthesis of nanoparticles. *Trends in Biotechnology* 31(4): 240-248.
- Kim, D., Jeong, S. and Moon, J. 2006. Synthesis of silver nanoparticles using the polyol process and the influence of precursor injection. *Nanotechnology* 17(16): 4019-4025.
- Kim, S., Choi, J. E., Choi, J., Chung, K., Park, K., Yi, J. and Ryu, D. 2009. Oxidative stress-dependent toxicity of silver nanoparticles in human hepatoma cells. *Toxicology in Vitro* 23(6): 1076-1084.
- Klein, T., Buhr, E. and Georg Frase, C. 2012. TSEM: A Review of scanning electron microscopy in transmission mode and its applications. *Advances in Imaging and Electron Physics* 171: 297-356.
- Kora, A. J., Sashidhar, R. and Arunachalam, J. 2012. Aqueous extract of gum olibanum (*Boswellia serrata*): A reductant and stabilizer for the biosynthesis of antibacterial silver nanoparticles. *Process Biochemistry* 47(10): 1516-1520.
- Kouvaris, P., Delimitis, A., Zaspalis, V., Papadopoulos, D., Tsipas, S. A. and Michailidis, N. 2012. Green synthesis and characterization of silver nanoparticles produced using *Arbutus Unedo* leaf extract. *Materials Letters* 76: 18-20.
- Krishnaraj, C., Jagan, E., Rajasekar, S., Selvakumar, P., Kalaichelvan, P. and Mohan, N. 2010. Synthesis of silver nanoparticles using *Acalypha indica* leaf extracts and its antibacterial activity against water borne pathogens. *Colloids and Surfaces B: Biointerfaces* 76(1): 50-56.
- Krishnaraj, C., Ramachandran, R., Mohan, K. and Kalaichelvan, P. 2012. Optimization for rapid synthesis of silver nanoparticles and its effect on phytopathogenic fungi. *Spectrochimica Acta Part A: Molecular and Biomolecular Spectroscopy* 93: 95-99.
- Kumar, R., Roopan, S. M., Prabhakarn, A., Khanna, V. G. and Chakroborty, S. 2012. Agricultural waste *Annona squamosa* peel extract: Biosynthesis of silver nanoparticles. *Spectrochimica Acta Part A: Molecular and Biomolecular Spectroscopy* 90: 173-176.
- Le, A.-T., Huy, P., Tam, P. D., Huy, T. Q., Cam, P. D., Kudrinskiy, A. and Krutyakov, Y. A. 2010. Green synthesis of finely-dispersed highly bactericidal silver nanoparticles via modified Tollens technique. *Current Applied Physics* 10(3): 910-916.
- Leela, A. and Vivekanandan, M. 2008. Tapping the unexploited plant resources for the synthesis of silver nanoparticles. *African Journal of Biotechnology* 7(17): 3162-3165.
- Li, Z., Wang, Y., Shen, J., Liu, W. and Sun, X. 2014. The measurement system of nanoparticle size distribution from dynamic light scattering data. *Optics and Lasers in Engineering* 56: 94-98.
- Liu, T., Zhong, J., Gan, X., Fan, C., Li, G. and Matsuda, N. 2003. Wiring electrons of cytochrome c with silver nanoparticles in layered films. *A European Journal of Chemical Physics and Physical Chemistry* 4(12): 1364-1366.
- Logeswari, P., Silambarasan, S. and Abraham, J. 2015. Synthesis of silver nanoparticles using plants extract

- and analysis of their antimicrobial property. Journal of Saudi Chemical Society 19(3): 311-317.
- Lukman, A. I., Gong, B., Marjo, C. E., Roessner, U. and Harris, A. T. 2011. Facile synthesis, stabilization, and anti-bacterial performance of discrete Ag nanoparticles using *Medicago sativa* seed exudates. Journal of Colloid and Interface Science 353(2): 433-444.
- Luo, X., Morrin, A., Killard, A. J. and Smyth, M. R. 2006. Application of nanoparticles in electrochemical sensors and biosensors. Electroanalysis 18(4): 319-326.
- Ma, L.N., Liu, D.J. and Wang, Z.X. 2014. Gold nanoparticle-based dynamic light scattering assay for mercury ion detection. Chinese Journal of Analytical Chemistry 42(3): 332-336.
- Maayan, G., Popovitz-Biro, R. and Neumann, R. 2006. Micelle directed synthesis of polyoxometalate nanoparticles and their improved catalytic activity for the aerobic oxidation of sulfides. Journal of the American Chemical Society 128(15): 4968-4969.
- Mafuné, F., Kohno, J., Takeda, Y., Kondow, T. and Sawabe, H. 2000. Formation and size control of silver nanoparticles by laser ablation in aqueous solution. The Journal of Physical Chemistry B 104(39): 9111-9117.
- Makarov, V., Love, A., Sinitsyna, O., Yaminsky, S. M. I., Taliany, M. and Kalinina, N. 2014. Green nanotechnologies: Synthesis of metal nanoparticles using plants. Acta Naturae 6(1): 35-44.
- Mallikarjuna, K., Dillip, Gr. R., Narasimha, G., Sushma, N. J. and Raju, B. D. P. 2012. Phytofabrication and characterization of silver nanoparticles from piper betle broth. Research Journal of Nanoscience and Nanotechnology 2(1): 17-23.
- Mallik, K., Mandal, M., Pradhan, N. and Pal, T. 2001. Seed mediated formation of bimetallic nanoparticles by UV irradiation: a photochemical approach for the preparation of "core-shell" type structures. Nano Letters 1(6): 319-322.
- Marambio-Jones, C. and Hoek, E. M. 2010. A review of the antibacterial effects of silver nanomaterials and potential implications for human health and the environment. Journal of Nanoparticle Research 12(5): 1531-1551.
- Marimuthu, S., Rahuman, A. A., Santhoshkumar, T., Jayaseelan, C., Kirthi, A. V., Bagavan, A., Kamaraj, C., Elango, G., Zahir, A. A. and Rajakumar, G. 2012. Lousicidal activity of synthesized silver nanoparticles using *Lawsonia inermis* leaf aqueous extract against *Pediculus humanus capitis* and *Bovicola ovis*. Parasitology Research 111(5): 2023-2033.
- Melchert, W. R., Reis, B. F. and Rocha, F. R. 2012. Green chemistry and the evolution of flow analysis. A review. Analytica Chimica Acta 714: 8-19.
- Meng, Y., Yao, C., Xue, S. and Yang, H. 2014. Application of Fourier transform infrared (FT-IR) spectroscopy in determination of microalgal compositions. Bioresource Technology 151: 347-354.
- Mie, R., Samsudin, M. W., Din, L. B., Ahmad, A., Ibrahim, N. and Adnan, S. N. A. 2014. Synthesis of silver nanoparticles with antibacterial activity using the lichen *Parmotrema praesorediosum*. International Journal of Nanomedicine 9: 121-127.
- Mittal, A. K., Bhaumik, J., Kumar, S. and Banerjee, U. C. 2014. Biosynthesis of silver nanoparticles: elucidation of prospective mechanism and therapeutic potential. Journal of Colloid and Interface Science 415: 39-47.
- Mittal, A. K., Chisti, Y. and Banerjee, U. C. 2013. Synthesis of metallic nanoparticles using plant extracts. Biotechnology Advances 31(2): 346-356.
- Mohan Kumar, K., Sinha, M., Mandal, B. K., Ghosh, A. R., Siva Kumar, K. and Sreedhara Reddy, P. 2012. Green synthesis of silver nanoparticles using *Terminalia chebula* extract at room temperature and their antimicrobial studies. Spectrochimica Acta Part A: Molecular and Biomolecular Spectroscopy 91: 228-233.
- Montazer, M., Alimohammadi, F., Shamei, A. and Rahimi, M. K. 2012. *In situ* synthesis of nano silver on cotton using Tollens' reagent. Carbohydrate Polymers 87(2): 1706-1712.
- Morones, J. R., Elechiguerra, J. L., Camacho, A., Holt, K., Kouri, J. B., Ramirez, J. T. and Yacaman, M. J. 2005. The bactericidal effect of silver nanoparticles. Nanotechnology 16(10): 2346-2353.
- MubarakAli, D., Thajuddin, N., Jeganathan, K. and Gunasekaran, M. 2011. Plant extract mediated synthesis of silver and gold nanoparticles and its antibacterial activity against clinically isolated pathogens. Colloids and Surfaces B: Biointerfaces 85(2): 360-365.
- Mukherjee, P., Ahmad, A., Mandal, D., Senapati, S., Sainkar, S. R., Khan, M. I., Parishcha, R., Ajaykumar, P., Alam, M. and Kumar, R. 2001. Fungus-mediated synthesis of silver nanoparticles and their immobilization in the mycelial matrix: a novel biological approach to nanoparticle synthesis. Nano Letters 1(10): 515-519.
- Nabikhan, A., Kandasamy, K., Raj, A. and Alikunhi, N. M. 2010. Synthesis of antimicrobial silver nanoparticles by callus and leaf extracts from saltmarsh plant, *Sesuvium portulacastrum* L. Colloids and Surfaces B: Biointerfaces 79(2): 488-493.
- Natrajan, K., Selvaraj, S. and Murty, R. V. 2010. Microbial production of silver nanoparticles. Digest Journal of Nanomaterials and Biostructures 5(1): 135-140.
- Nazeruddin, G., Prasad, N., Waghmare, S., Garadkar, K. and Mulla, I. 2014. Extracellular biosynthesis of silver nanoparticle using *Azadirachta indica* leaf extract and its antimicrobial activity. Journal of Alloys and Compounds 583: 272-277.
- Pal, S., Tak, Y. K. and Song, J. M. 2007. Does the antibacterial activity of silver nanoparticles depend on the shape of the nanoparticle? A study of the gram-negative bacterium *Escherichia coli*. Applied and Environmental Microbiology 73(6): 1712-1720.
- Panáček, A., Kvitek, L., Pucek, R., Kolar, M., Vecerova, R., Pizurova, N., Sharma, V. K., Nevečná, T. j. and Zboril, R. 2006. Silver colloid nanoparticles: synthesis, characterization, and their antibacterial

- activity. The Journal of Physical Chemistry B 110(33): 16248-16253.
- Pandian, M., Marimuthu, R., Natesan, G. and Rajagopal, R. E. 2013. Development of biogenic silver nanoparticle from *Pelargonium graveolens* leaf extract and their antibacterial activity. American Journal of Nanoscience and Nanotechnology 1(2): 57-64.
- Patil, C. D., Patil, S. V., Borase, H. P., Salunke, B. K. and Salunkhe, R. B. 2012. Larvicidal activity of silver nanoparticles synthesized using *Plumeria rubra* plant latex against *Aedes aegypti* and *Anopheles stephensi*. Parasitology Research 110(5): 1815-1822.
- Philip, D. 2010. Green synthesis of gold and silver nanoparticles using *Hibiscus rosa sinensis*. Physica E: Low-dimensional Systems and Nanostructures 42(5): 1417-1424.
- Philip, D., Unni, C., Aromal, S. A. and Vidhu, V. 2011. *Murraya koenigii* leaf-assisted rapid green synthesis of silver and gold nanoparticles. Spectrochimica Acta Part A: Molecular and Biomolecular Spectroscopy 78(2): 899-904.
- Prabhu, D., Arulvasu, C., Babu, G., Manikandan, R. and Srinivasan, P. 2013. Biologically synthesized green silver nanoparticles from leaf extract of *Vitex negundo* L. induce growth-inhibitory effect on human colon cancer cell line HCT15. Process Biochemistry 48(2): 317-324.
- Prabhu, S. and Poulouse, E. K. 2012. Silver nanoparticles: mechanism of antimicrobial action, synthesis, medical applications, and toxicity effects. International Nano Letters 2(1): 1-10.
- Raja, K., Saravanakumar, A. and Vijayakumar, R. 2012. Efficient synthesis of silver nanoparticles from *Prosopis juliflora* leaf extract and its antimicrobial activity using sewage. Spectrochimica Acta Part A: Molecular and Biomolecular Spectroscopy 97: 490-494.
- Rajakumar, G. and Abdul Rahuman, A. 2011. Larvicidal activity of synthesized silver nanoparticles using *Eclipta prostrata* leaf extract against filariasis and malaria vectors. Acta Tropica 118(3): 196-203.
- Rajasekharreddy, P., Rani, P. U. and Sreedhar, B. 2010. Qualitative assessment of silver and gold nanoparticle synthesis in various plants: a photobiological approach. Journal of Nanoparticle Research 12(5): 1711-1721.
- Ramamurthy, C., Padma, M., Mareeswaran, R., Suyavaran, A., Kumar, M. S., Premkumar, K. and Thirunavukkarasu, C. 2013. The extra cellular synthesis of gold and silver nanoparticles and their free radical scavenging and antibacterial properties. Colloids and Surfaces B: Biointerfaces 102: 808-815.
- Raman, N., Sudharsan, S., Veerakumar, V., Pravin, N. and Vithiya, K. 2012. *Pithecellobium dulce* mediated extra-cellular green synthesis of larvicidal silver nanoparticles. Spectrochimica Acta Part A: Molecular and Biomolecular Spectroscopy 96: 1031-1037.
- Ramteke, C., Chakrabarti, T., Sarangi, B. K. and Pandey, R. 2013. Synthesis of silver nanoparticles from the aqueous extract of leaves of *Ocimum sanctum* for enhanced antibacterial activity. Journal of Chemistry doi:10.1155/2013/278925.
- Rodríguez-León, E., Iñiguez-Palomares, R., Navarro, R. E., Herrera-Urbina, R., Tánori, J., Iñiguez-Palomares, C. and Maldonado, A. 2013. Synthesis of silver nanoparticles using reducing agents obtained from natural sources (*Rumex hymenosepalus* extracts). Nanoscale Research Letters 8(1): 1-9.
- Roopan, S. M., Madhumitha, G., Rahuman, A. A., Kamaraj, C., Bharathi, A. and Surendra, T. 2013. Low-cost and eco-friendly phyto-synthesis of silver nanoparticles using *Cocos nucifera* coir extract and its larvicidal activity. Industrial Crops and Products 43: 631-635.
- Sable, N., Gaikwad, S., Bonde, S., Gade, A. and Rai, M. 2012. Phytofabrication of silver nanoparticles by using aquatic plant *Hydrilla verticillata*. Nusantara Bioscience 4: 45-49.
- Saifuddin, N., Wong, C. and Yasumira, A. 2009. Rapid biosynthesis of silver nanoparticles using culture supernatant of bacteria with microwave irradiation. Journal of Chemistry 6(1): 61-70.
- Santhoshkumar, T., Rahuman, A. A., Bagavan, A., Marimuthu, S., Jayaseelan, C., Kirthi, A., Kamaraj, C., Rajakumar, G., Zahir, A. A. and Elango, G. 2012. Evaluation of stem aqueous extract and synthesized silver nanoparticles using *Cissus quadrangularis* against *Hippobosca maculata* and *Rhipicephalus* (Boophilus) microplus. Experimental Parasitology 132(2): 156-165.
- Sastry, M., Ahmad, A., Islam Khan, M. and Kumar, R. 2003. Biosynthesis of metal nanoparticles using fungi and actinomycete. Current Science 85(2): 162-170.
- Satyavani, K., Ramanathan, T. and Gurudeeban, S. 2011. Plant mediated synthesis of biomedical silver nanoparticles by using leaf extract of *Citrullus colocynthis*. Research Journal of Nanoscience and Nanotechnology 1(2): 95-101.
- Sen, P., Ghosh, J., Abdullah, A. and Kumar, P. 2003. Preparation of Cu, Ag, Fe and Al nanoparticles by the exploding wire technique. Journal of Chemical Sciences 115(5-6): 499-508.
- Shahverdi, A. R., Minaeian, S., Shahverdi, H. R., Jamalifar, H. and Nohi, A.-A. 2007. Rapid synthesis of silver nanoparticles using culture supernatants of Enterobacteria: A novel biological approach. Process Biochemistry 42(5): 919-923.
- Shaligram, N. S., Bule, M., Bhambure, R., Singhal, R. S., Singh, S. K., Szakacs, G. and Pandey, A. 2009. Biosynthesis of silver nanoparticles using aqueous extract from the compactin producing fungal strain. Process Biochemistry 44(8): 939-943.
- Sharma, V. K., Yngard, R. A. and Lin, Y. 2009. Silver nanoparticles: green synthesis and their antimicrobial activities. Advances in Colloid and Interface Science 145(1): 83-96.
- Sheny, D., Mathew, J. and Philip, D. 2011. Phytosynthesis of Au, Ag and Au-Ag bimetallic nanoparticles using aqueous extract and dried leaf of *Anacardium occidentale*. Spectrochimica Acta Part A: Molecular and Biomolecular Spectroscopy 79(1): 254-262.
- Shin, H. S., Yang, H. J., Kim, S. B. and Lee, M. S. 2004.

- Mechanism of growth of colloidal silver nanoparticles stabilized by polyvinyl pyrrolidone in γ -irradiated silver nitrate solution. *Journal of Colloid and Interface Science* 274(1): 89-94.
- Silvestre, C., Duraccio, D. and Cimmino, S. 2011. Food packaging based on polymer nanomaterials. *Progress in Polymer Science* 36(12): 1766-1782.
- Singh, C., Sharma, V., Naik, P., Khandelwal, V. and Singh, H. 2011. A green biogenic approach for synthesis of gold and silver nanoparticles using *Zingiber officinale*. *Digest Journal of Nanomaterials and Biostructures* 6(2): 535-542.
- Sivakumar, P., Nethradevi, C. and Renganathan, S. 2012. Synthesis of silver nanoparticles using *Lantana camara* fruit extract and its effect on pathogens. *Asian Journal of pharmaceutical and Clinical Research* 5(3): 97-101.
- Sondi, I. and Salopek-Sondi, B. 2004. Silver nanoparticles as antimicrobial agent: a case study on *E. coli* as a model for Gram-negative bacteria. *Journal of Colloid and Interface Science* 275(1): 177-182.
- Song, J. Y., Jang, H. and Kim, B. S. 2009. Biological synthesis of gold nanoparticles using *Magnolia kobus* and *Diopyros kaki* leaf extracts. *Process Biochemistry* 44(10): 1133-1138.
- Song, J. Y. and Kim, B. S. 2009. Rapid biological synthesis of silver nanoparticles using plant leaf extracts. *Bioprocess and Biosystems Engineering* 32(1): 79-84.
- Sukirtha, R., Priyanka, K. M., Antony, J. J., Kamalakkannan, S., Thangam, R., Gunasekaran, P., Krishnan, M. and Achiraman, S. 2012. Cytotoxic effect of green synthesized silver nanoparticles using *Melia azedarach* against *in vitro* HeLa cell lines and lymphoma mice model. *Process Biochemistry* 47(2): 273-279.
- Sulaiman, G. M., Mohammed, W. H., Marzoog, T. R., Al-Amiery, A. A. A., Kadhum, A. A. H. and Mohamad, A. B. 2013. Green synthesis, antimicrobial and cytotoxic effects of silver nanoparticles using *Eucalyptus chapmaniana* leaves extract. *Asian Pacific Journal of Tropical Biomedicine* 3(1): 58-63.
- Sulochana, S., Krishnamoorthy, P. and Sivaranjani, K. 2012. Synthesis of silver nanoparticles using leaf extract of *Andrographis paniculata*. *Journal of Pharmacology & Toxicology* 7(5): 251-258.
- Suman, T., Radhika Rajasree, S., Kanchana, A. and Elizabeth, S. B. 2013. Biosynthesis, characterization and cytotoxic effect of plant mediated silver nanoparticles using *Morinda citrifolia* root extract. *Colloids and Surfaces B: Biointerfaces* 106: 74-78.
- Sun, Q., Cai, X., Li, J., Zheng, M., Chen, Z. and Yu, C.-P. 2014. Green synthesis of silver nanoparticles using tea leaf extract and evaluation of their stability and antibacterial activity. *Colloids and Surfaces A: Physicochemical and Engineering Aspects* 444: 226-231.
- Tanaka, N. 2008. Present status and future prospects of spherical aberration corrected TEM/STEM for study of nanomaterials. *Science and Technology of Advanced Materials* 9 (1): doi: 10.1088/1468-6996/9/1/014111.
- Thirumalai Arasu, V., Prabhu, D. and Soniya, M. 2010. Stable silver nanoparticle synthesizing methods and its applications. *Research Journal of Biological Science* 1: 259-270.
- Thirunavoukkrasu, M., Balaji, U., Behera, S., Panda, P. and Mishra, B. 2013. Biosynthesis of silver nanoparticle from leaf extract of *Desmodium gangeticum*(L.) DC. and its biomedical potential. *Spectrochimica Acta Part A: Molecular and Biomolecular Spectroscopy* 116: 424-427.
- Tolaymat, T. M., El Badawy, A. M., Genaidy, A., Scheckel, K. G., Luxton, T. P. and Suidan, M. 2010. An evidence-based environmental perspective of manufactured silver nanoparticle in syntheses and applications: a systematic review and critical appraisal of peer-reviewed scientific papers. *Science of the Total Environment* 408(5): 999-1006.
- Tran, T. T. T., Vu, T. T. H. and Nguyen, T. H. 2013. Biosynthesis of silver nanoparticles using *Tithonia diversifolia* leaf extract and their antimicrobial activity. *Materials Letters* 105: 220-223.
- Travan, A., Pelillo, C., Donati, I., Marsich, E., Benincasa, M., Scarpa, T., Semeraro, S., Turco, G., Gennaro, R. and Paoletti, S. 2009. Non-cytotoxic silver nanoparticle-polysaccharide nanocomposites with antimicrobial activity. *Biomacromolecules* 10(6): 1429-1435.
- Troupis, A., Hiskia, A. and Papaconstantinou, E. 2002. Synthesis of metal nanoparticles by using polyoxometalates as photocatalysts and stabilizers. *Angewandte Chemie International Edition* 41(11): 1911-1914.
- Tuoriniemi, J., Cornelis, G. and Hassellöv, M. 2012. Size discrimination and detection capabilities of single-particle ICPMS for environmental analysis of silver nanoparticles. *Analytical Chemistry* 84(9): 3965-3972.
- Uchida, S., Hikichi, S., Akatsuka, T., Tanaka, T., Kawamoto, R., Lesbani, A., Nakagawa, Y., Uehara, K. and Mizuno, N. 2007. Preparation of monodispersed nanoparticles by electrostatic assembly of kegg-in-type polyoxometalates and 1, 4, 7-triazacyclononane-based transition-metal complexes. *Chemistry of Materials* 19(19): 4694-4701.
- Usha Rani, P. and Rajasekharreddy, P. 2011. Green synthesis of silver-protein (core-shell) nanoparticles using Piper betle L. leaf extract and its ecotoxicological studies on *Daphnia magna*. *Colloids and Surfaces A: Physicochemical and Engineering Aspects* 389(1): 188-194.
- Vadlapudi, V. and Kaladhar, D. 2014. Review: reen synthesis of silver and gold nanoparticles. *Middle-East Journal of Scientific Research* 19(6): 834-842.
- Valli, J. S. and Vaseeharan, B. 2012. Biosynthesis of silver nanoparticles by *Cissus quadrangularis* extracts. *Materials Letters* 82: 171-173.
- Valodkar, M., Nagar, P. S., Jadeja, R. N., Thounaojam, M. C., Devkar, R. V. and Thakore, S. 2011. Euphorbiaceae latex induced green synthesis of non-cytotoxic metallic nanoparticle solutions: a rational approach

- to antimicrobial applications. *Colloids and Surfaces A: Physicochemical and Engineering Aspects* 384(1): 337-344.
- Vanaja, M. and Annadurai, G. 2013. *Coleus aromaticus* leaf extract mediated synthesis of silver nanoparticles and its bactericidal activity. *Applied Nanoscience* 3(3): 217-223.
- Velayutham, K., Rahuman, A. A., Rajakumar, G., Roopan, S. M., Elango, G., Kamaraj, C., Marimuthu, S., Santhoshkumar, T., Iyappan, M. and Siva, C. 2013. Larvicidal activity of green synthesized silver nanoparticles using bark aqueous extract of *Ficus racemosa* against *Culex quinquefasciatus* and *Culex gelidus*. *Asian Pacific journal of Tropical Medicine* 6(2): 95-101.
- Vigneshwaran, N., Ashtaputre, N., Varadarajan, P., Nachane, R., Paralikar, K. and Balasubramanya, R. 2007. Biological synthesis of silver nanoparticles using the fungus *Aspergillus flavus*. *Materials Letters* 61(6): 1413-1418.
- Vijay Kumar, P., Pammi, S., Kollu, P., Satyanarayana, K. and Shameem, U. 2014. Green synthesis and characterization of silver nanoparticles using *Boerhaavia diffusa* plant extract and their anti bacterial activity. *Industrial Crops and Products* 52: 562-566.
- Vijayakumar, M., Priya, K., Nancy, F., Noorlidah, A. and Ahmed, A. 2013. Biosynthesis, characterisation and anti-bacterial effect of plant-mediated silver nanoparticles using *Artemisia nilagirica*. *Industrial Crops and Products* 41: 235-240.
- Vivek, R., Thangam, R., Muthuchelian, K., Gunasekaran, P., Kaveri, K. and Kannan, S. 2012. Green biosynthesis of silver nanoparticles from *Annona squamosa* leaf extract and its *in vitro* cytotoxic effect on MCF-7 cells. *Process Biochemistry* 47(12): 2405-2410.
- Wilson, D. and Langell, M. 2014. XPS analysis of oleylamine/oleic acid capped Fe₃O₄ nanoparticles as a function of temperature. *Applied Surface Science* 303: 6-13.
- Xiong, J., Wu, X. and Xue, Q. 2013. One-step route for the synthesis of monodisperse aliphatic amine-stabilized silver nanoparticles. *Colloids and Surfaces A: Physicochemical and Engineering Aspects* 423: 89-97.
- Yang, N. and Li, W. 2013. Mango peel extract mediated novel route for synthesis of silver nanoparticles and antibacterial application of silver nanoparticles loaded onto non-woven fabrics. *Industrial Crops and Products* 48: 81-88.
- Yin, Y., Li, Z.-Y., Zhong, Z., Gates, B., Xia, Y. and Venkateswaran, S. 2002. Synthesis and characterization of stable aqueous dispersions of silver nanoparticles through the Tollens process. *Journal of Materials Chemistry* 12(3): 522-527.
- Zayed, M. F., Eisa, W. H. and Shabaka, A. 2012. Malva parviflora extract assisted green synthesis of silver nanoparticles. *Spectrochimica Acta Part A: Molecular and Biomolecular Spectroscopy* 98: 423-428.
- Zhang, Y., Cheng, X., Zhang, Y., Xue, X. and Fu, Y. 2013. Biosynthesis of silver nanoparticles at room temperature using aqueous aloe leaf extract and antibacterial properties. *Colloids and Surfaces A: Physicochemical and Engineering Aspects* 423: 63-68.